





ECO PASSPORT E24HPDLE8 AITEX

www.oeko-tex.com

Reach out to the Dyesyn team to explore how the adoption of Dyesyn Reactive Dyes technology can elevate the performance of your business.




## Contact Us

**E-Mail**: info@dyesyn.com **Website**: www.dyesyn.com **Address**: Aydınlı SB Mh. 3. Sk. DESBAŞ No: 2 İç Kapı Z02

Tuzla / İstanbul / Türkiye





Ecolocigal profile / Metal complex		Chlorinated water	Dry cleaning		Perspiration (Alkaline)		Perspiration (Acid)		Washing			Water		Oxidative bleach		Perspiration light alkaline	G. S.	Perspiration light acid		Light	Full shade liquid g/kg	Full shade powder g/kg	Full shade	
nplex	ISO 105:E03 20 ppm active cholorine		ISO 105:D01		ISO 105:E04		ISO 105:E04		ISO C06:A2S 40 °C		ISO 105:E01		ISO 105:C09		ISO 105:B07		ISO 105:B07		ISO 105:B02				DYESYN REACTIVE DYE FOR TEXTILE PRINTING Fastness Properties	OEKO TEX®  ECO PASSPORT  www.oeko-tex.com
	1:9	Stock color	Stock color	Stock color	Stock color	Stock color	Stock color	Stock color	Stock color	Stock color	Stock color	Stock color	1:9	Stock color	1:9	Stock color	1:9	Stock color	1:9	Stock color				
	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4	4-5	5	6	65	30		DYESYN YELLOW P-6GS
	4	4	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4	4-5	51	o	66			DYESYN GOLDEN YELLOW P-2RN
	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	3-4	ω	4	3-4	4-5	40	30		DYESYN ORANGE P-2R
	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4	4-5	5	6	55	30		DYESYN ORANGE P-4R
	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5	4-5	3-4	4	3-4	4-5	4	5		30		DYESYN RED P-6B
	4	4	4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5	4-5	ω	3-4	ယ	4	3-4	4-5	75	30		DYESYN RED P-BN
	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4	4	4	4-5	4-5	ω	3-4	ω	4	3-4	4-5	60			DYESYN RED P-4BN
	2	2-3	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4	4-5	4	4-5	5-6	6	65	30		DYESYN BLUE P-3R
Cu	1-2	2-3	4-5	4-5	4	4	4	4	4	4	4	4	4	4	သ	4	3-4	4	4	5-6	75	30		DYESYN TURQUOISE P-GR
	6	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	e	4	20	3-4	110	3-4	3.	4-5	100	40		DYESYN NAVY P-2R
	ē	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	Ē	4	3	3-4	· ·	3-4	ž	4-5		20		DYESYN NAVY P-2R HC
Cu	E	N	4	4-5	4	4-5	4	4-5	4-5	4-5	4-5	4-5	1	4	1	4	1	4	•	5-6		40		DYESYN BLUE P-5R
	4	4	4-5	4-5	4	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	3-4	4	3-4	4	4	0	60			DYESYN BROWN P-2R
Cr/Co	1-2	2-3	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	ω	ω	ω	3-4	3-4	4	5	5-6	30			DYESYN BLACK P-SG
	<b>N</b> 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	E	4	ж	4	к	4	а	O1	175	50		DYESYN BLACK P-GR
Cr / Co	1-2	ω	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	ω	ယ	ω	3-4	3-4	4	5	5-6	30	15		DYESYN BLACK VTN
Cr / Co	1-2	ω	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	ω	ω	ω	3-4	3-4	4	Si Si	5-6	30	15		DYESYN BLACK DNN